

SPECIFICATION SHEET FOR 7/16" 250K STRAND

PC Strand to ASTM A416

Strand size	7/16" 250K Low Relaxation	
Nominal Strand Diameter	0.438"	11.11 mm
Minimum Breaking Strength	27,000 lbf	120.1 kN/12,247 kgf
Minimum Yield Point At 1% Extension	24,300 lbf	108.1 kN/11,022 kgf
Minimum Elongation In 24" Gauge Length	3.5%	
Minimum Diameter Difference C/W and O/W	0.0028 in	0.07 mm
Nominal Modulus Of Elasticity*	28.6 x 10 ⁶ PSI	197.2 kN/mm ² 20,120 kg/mm ²
Nominal Area	0.108 in ²	69.68 mm ²
Nominal Strand Pitch	6.50 in	165 mm
Straightness Max*	1" over 4 ft	25 mm over 1,200 mm
Nominal Weight	367 lbs/1,000 ft	548 kg/1,000 M

NOOR-National Office of Raw Materials of Pre-stressing Systems, LLC.

Headquarter Office:

1133 Broadway, Manhattan, Suite 706,
New York, NY10010 .USA
Tel: +1 (212) 631 5819
Fax: +1 (212) 631 5820
www.noorprestressing.com

Australia:

88 Phillip St, Sydney, NSW 2000,
Fax: +6 (128) 0886 195
mtest@noorps.com
tsupport@noorps.com
www.noorps.com