

## SPECIFICATION SHEET FOR 9/16" 270K STRAND

### PC Strand to ASTM A416

Strand size	9/16" 270K Low Relaxation	
Nominal Strand Diameter	0.563"	14.29 mm
Minimum Breaking Strength	51,700 lbf	223.0 kN/23,451 kgf
Minimum Yield Point At 1% Extension	46,530 lbf	207.0 kN/21,106 kgf
Minimum Elongation In 24" Gauge Length	3.5%	
Minimum Diameter Difference C/W and O/W	0.004 in	0.011 mm
Nominal Modulus Of Elasticity*	28.5 x 10 <sup>6</sup> PSI	195.2 kN/mm <sup>2</sup> 19,900 kg/mm <sup>2</sup>
Nominal Area	0.1932 in <sup>2</sup>	124.6 mm <sup>2</sup>
Nominal Strand Pitch	7.88 in	200 mm
Straightness Max*	1" over 4 ft	25 mm over 1,200 mm
Nominal Weight	655 lbs/1,000 ft	977 kg/1,000 M

NOOR-National Office of Raw Materials of Pre-stressing Systems, LLC.

**Headquarter Office:**

1133 Broadway, Manhattan, Suite 706,  
New York, NY10010 .USA  
Tel: +1 (212) 631 5819  
Fax: +1 (212) 631 5820  
[www.noorprestressing.com](http://www.noorprestressing.com)

**Australia:**

88 Phillip St, Sydney, NSW 2000,  
Fax: +6 (128) 0886 195  
[mttest@noorps.com](mailto:mttest@noorps.com)  
[tsupport@noorps.com](mailto:tsupport@noorps.com)  
[www.noorps.com](http://www.noorps.com)